



## TECHNICAL DATA SHEET

### Textol CF Premium

Premium quality full synthetic lubricant for chain lubrication for temperatures > 240° C with viscosity 260

#### PRODUCT DESCRIPTION

- + High performance lubricating oil for the chain lubrication
- + based on synthetic ester
- + suitable for very high operating temperatures
- + low residue formation
- + stable against oxidation
- + excellent adhesion of the lubricating film
- + contains EP-additives for wear-protection

#### CHARACTERISTICS

Colour / DIN ISO 2049	L 2.5
Density/15°C / DIN EN ISO 12185	960 kg/m <sup>3</sup>
Viscosity/40°C / ASTM D 7042	260 mm <sup>2</sup> /s
Flash point (Cleveland) / DIN ISO 2592	260 °C

#### APPLICATION

**Textol CF Premium** is a premium quality full synthetic lubricant for high temperatures. Extreme pressure additives provide excellent wear protection and minimize equipment maintenance.

**Textol CF Premium** is used for general chain lubrication as well as for special intended uses, such as lubrication of mechanically and thermally highly stressed drive chains in drying machines in the textile industry.

#### STORAGE

To avoid the insertion of humidity or contaminations, pay attention that the package is closed immediately after withdrawal!

26410

09/2019-26410-6

The statements made in this publication are according to our present knowledge. They do not absolve the user from own examinations. A legally binding assurance of certain properties or suitability for a specific use can not be derived from our statements. Possibly existing laws and regulations concerning the handling and use of our products have to be observed by the receiver of our products himself.



## TECHNICAL DATA SHEET

### Textol CF Premium

Premium quality full synthetic lubricant for chain lubrication for temperatures > 240° C with viscosity 260

Recommended storage temperature: +10 °C up to +40 °C.

Benefit from our service, we will gladly advise you and develop individual application recommendations for your process. Please also note the material safety data sheet.

26410

09/2019-26410-6

The statements made in this publication are according to our present knowledge. They do not absolve the user from own examinations. A legally binding assurance of certain properties or suitability for a specific use can not be derived from our statements. Possibly existing laws and regulations concerning the handling and use of our products have to be observed by the receiver of our products himself.

2 / 2