

Technical Data Sheet

Multicor LF 65 Plus

Product description

- solvent-free anti-corrosion agent
- on the basis of mineral oil
- neutral odour
- outstanding corrosion protection
- free of barium

Characteristics

Colour / DIN ISO 2049:	lighter 4.5
Density/15°C / DIN EN ISO 12185:	860 kg/m ³
Viscosity/20°C / ASTM D 7042 :	62 mm ² /s
Flash point (Cleveland) / DIN ISO 2592:	> 180 °C
Type of protective film:	oily
Colour of the protective film:	transparent
Kesternich test / DIN EN ISO 6270-2:	39 cycles
Salt spray test / DIN EN ISO 9227:	32 hour(s)

Application

Multicor LF 65 Plus is an anti-corrosion oil of medium viscosity for the temporary conservation of coated and uncoated steel qualities. The product is mainly used in rolling mills.

Multicor LF 65 Plus can be applied by spraying, rolling or dipping. Electrostatic application is also possible.

Concerning the electrostatic application, we suggest heating up the product in the tank to 50 - 60 °C. In heated tanks **Multicor LF 65 Plus** should constantly be circulated to guarantee a uniform temperature distribution.

Degreasing

We recommend degreasing with aqueous-alkaline as well as solvent cleaners.

27370

04/2017-27370-4

The statements made in this publication are according to our present knowledge. They do not absolve the user from own examinations. A legally binding assurance of certain properties or suitability for a specific use can not be derived from our statements. Possibly existing laws and regulations concerning the handling and use of our products have to be observed by the receiver of our products himself.

1 / 2

Technical Data Sheet

Multicor LF 65 Plus

Storage

We recommend a storage temperature of +15° C to +40 °C.

27370

04/2017-27370-4

The statements made in this publication are according to our present knowledge. They do not absolve the user from own examinations. A legally binding assurance of certain properties or suitability for a specific use can not be derived from our statements. Possibly existing laws and regulations concerning the handling and use of our products have to be observed by the receiver of our products himself.

2 / 2